



TECHNICAL INFORMATION

INTERFOAM WP-6017FR POLYOL

Description

Interfoam WP-6017FR Polyol is a polyol for water-blown, flame-retardant polyurethane foam in roofing and continuous panel applications. It reacts with isocyanate to produce a foam with excellent flow, uniform cell structure, and strong adhesion to steel and paper. The resulting foam has excellent dimensional stability and good strength. This polyol uses only water as the blowing agent.

Physical Properties

Appearance:	Yellow liquid without any deposit
Viscosity (25°C):	400±200
Specific gravity (25°C):	1.02

Formulation and Reactivity

Components	Part by Weight
Interfoam WP-6017FR Polyol	100
pMDI	130-160

Reactivity	Unit	Range
<i>Hand mixing ≥2000rpm for 3 seconds (raw materials at 30-35°C, room temp. at 25°C)</i>		
Cream Time	s	5-7
Gel Time	s	21-36
Tack Free Time	s	35-45
Free Rise Density	kg/m ³	16±0.5

Below are physical performance test results from the lab using high pressure machine sample test (core density 28.0 kg/m³):

10% compressive strength:	108 Kpa
K-factor (25 °C):	22.2 mW/m.K

Dimensional stability (after 48h test, %):

	Length	Breadth	Thickness
-20 °C	-0.26	-0.29	-0.45
50 °C	-0.41	-0.15	-0.26

Storage Condition

Interfoam WP-6017FR Polyol product has a shelf life of 6 months from the date of manufacture, provided it is stored in factory-packed containers and protected against extreme weather conditions, particularly heat and moisture. The optimum storage temperature of Interfoam WP-6017FR Polyol product is between 5°C and 30°C. Lower and higher storage temperatures are not preferable and should be avoided.

Safety and Information

Considering the composition of Interfoam WP-6017FR Polyol product and extensive manufacturing and usage experience with similar products, it has been observed that there is no significant risk to user health, although certain ingredients in the mixture can pose mild toxicity risks if swallowed or inhaled and may cause skin and eye irritation. Therefore, handling of these products should adhere to standard industrial hygiene practices, including the use of appropriate protective clothing, goggles, and ensuring adequate ventilation. In case of skin contact, wash the affected area with soap and water. If in contact with eyes, rinse thoroughly with plenty of water and seek medical attention if irritation persists. It is advisable for individuals who suffer accidental injury to be examined by a doctor. Additionally, be aware of fire and explosion hazards associated with the product.